

# EZ KOTE 1004

## Physical Properties:

- Appearance: Gray Black Slurry
- Baume: 50° - 55°
- Density: 9.5 lbs. – 10.2 lbs./gal
- Solids Level: 32% - 38%

## PACKAGING:

Totes  
Drums

## DESCRIPTION:

**EZ KOTE 1004** is a high refractory/graphite modified coating designed for both ferrous and non-ferrous applications. **EZ KOTE 1004** can be applied by brushing, dipping, or spraying. The rheological properties of **EZ KOTE 1004** contribute to improved workability and consistency, thus providing improved surface finish and casting quality. Because of the excellent suspension of **EZ KOTE 1004** minimal settling occurs which allows for easy redispersion. The coating is designed to be reduced with water at the customer's facility.

## APPLICATION PROPERTIES

Baume

## FLOW COAT PARAMETERS

35° - 40°

## BRUSH/SWAB

Baume: 40° - 45°

## SPRAY

35° - 40°

## DIP

16° - 20°

\*General properties, not specifications

## DIRECTIONS FOR USE:

**EZ KOTE 1004** should be mixed with a pneumatic or an electric mixer. Material must be mixed thoroughly in its container before diluting.

**EZ KOTE 1004** is designed to be diluted by the customer to its proper specification according to the application. **EZ KOTE 1004** must be torch or oven dried prior to casting.

